

COMPOSITION

Synthetic membrane of plasticised PVC with signal layer. Reinforced with a polyester mesh. Manufactured in UNI EN ISO 9001 and UNI EN ISO 14001 certified plant. Resistant to weathering and ultraviolet rays. UEAtc certified. Laying by installers approved by Flag S.p.A. Finishing and accessories with elements manufactured and approved by Flag S.p.A.

FEATURES

- Resistance to wind stress
- High resistance to weathering and ultraviolet rays.
- High mechanical resistance.
- Insensitivity to the hot-cold cycles
- Resistance to puncturing
- Possible RAL color for landscape or architectural purpose

AREA OF USE

ROOFING

- Mechanical Fastening System:
 - Mechanical fixing

PHYSICAL-CHEMICAL PROPERTIES

	FLAGON SR 120	FLAGON SR 150	FLAGON SR 180	FLAGON SR 200	FLAGON SR 240	Testing method
Thickness (mm)	1,2	1,5	1,8	2,0	2,4	UNI EN 1849 - 2
Weight (Kg/m ²)	1,50	1,80	2,15	2,40	2,90	UNI EN 1849 - 2
Tensile strenght (rectangular test specimen) (N/5cm)	≥ 1100	≥ 1100	≥ 1100	≥ 1100	≥ 1100	UNI EN 12311 - 2
• average production value	L. 1278 T. 1285	L. 1296 T. 1267	L. 1306 T. 1281	L. 1292 T. 1269	L. 1278 T. 1305	
• standard deviation	L. 31,4 T. 29,8	L. 32,1 T. 27,4	L. 30,8 T. 25,7	L. 30,2 T. 26,1	L. 28,9 T. 26,8	
Elongation to break (rectangular test specimen) (%)	≥ 15	≥ 15	≥ 15	≥ 15	≥ 15	UNI EN 12311 - 2
• average production value	L. 20 T. 20	L. 20 T. 20	L. 20 T. 20	L. 20 T. 20	L. 20 T. 20	
• standard deviation	L. 0,5 T. 0,5	L. 0,5 T. 0,48	L. 0,5 T. 0,45	L. 0,5 T. 0,5	L. 0,5 T. 0,5	
Tear resistance (N)	≥ 200	≥ 200	≥ 200	≥ 200	≥ 200	UNI EN 12310 - 2
Puncture resistance (mm)	≥ 450	≥ 800	≥ 900	≥ 1000	≥ 1500	DIN 16726-5.12
Cold bending (°C)	≤ - 25	≤ - 25	≤ - 25	≤ - 25	≤ - 25	UNI EN 495 - 5
Hydrostatic pressure resistance (6 hours at 0,5 MPa)	waterproof	waterproof	waterproof	waterproof	waterproof	UNI EN 1928 meth. B
Dimensional stability after 6 hours at 80°C (%)	≤ ± 0,5	≤ ± 0,5	≤ ± 0,5	≤ ± 0,5	≤ ± 0,5	UNI EN 1107 - 2
Resistance to artificial weathering	no cracking	no cracking	no cracking	no cracking	no cracking	UNI EN 1297
Root resistance	no penetration	no penetration	no penetration	no penetration	no penetration	DIN 4062
Resistance to hail on rigid substrate (m/s)	≥ 25	≥ 25	≥ 25	≥ 25	≥ 25	UNI 13583
Thermal ageing in air after 168 d at 70°C						
Cold bending (°C)	≤ - 25	≤ - 25	≤ - 25	≤ - 25	≤ - 25	UNI EN 1296
Peel resistance of joints (N/50 mm)	≥ 150	≥ 150	≥ 150	≥ 150	≥ 150	UNI EN 12316 - 2
Shear resistance of joints	breaking out of joint	breaking out of joint	breaking out of joint	breaking out of jointof	breaking out of jointof	UNI EN 12317 - 2
Resistance to impact (mm)	10	10	10	10	10	UNI EN 12691
Resistance to static punching (kg)	≥ 20	≥ 20	≥ 20	≥ 20	≥ 20	UNI EN 12316

PRODUCTION STANDARD

Thickness	1,2 mm	1,5 mm	1,8 mm	2,0 mm	2,4 mm	
Width	1,60 or 2,10 m	1,60 or 2,10 m	1,60 or 2,10 m	1,60 or 2,10 m	1,60 or 2,10 m	
Length	20 m	20 m	20 m	20 m	20 m	
Colour	Light grey					

Due to its formulation, the liner is NOT subject to the requirements set forth in the EEC 79/831 regulation on dangerous substances. If the product should be disposed of as waste, we recommend sending it to an authorised landfill site or to an incinerator equipped with post-combustion chamber and fume washing system.



FLAG GROUP